TOSHIBA

Technical Data Coin-type Manganese Dioxide Lithium Battery

Type: CR1220

Made in China

2022.Ver1.0

TOSHIBA LIFESTYLE PRODUCTS & SERVICES CORPORATION

TOSHIBA

Ratings

Battery system Item		Coin-type Manganese Dioxide Lithium Battery		
Battery type		CR1220		
Nominal Voltage		3.0V		
Standard Capacity [Condition]		40 mAh [on continuous discharge under 62k load to 2.0V end-point at 20deg.C]		
Terminals	Cap Terminals	SUS + Ni plate		
	Base Terminals	SUS + Ni plate		
Outer dimensions	Diameter	φ12.5(0/-0.3)mm		
	Overall height	2.0(0/-0.2)mm		
Usable temperature range				
Storage temperature range		-20 ~ 65deg.C		

This is only for reference.(not guaranteed.) This information contained herein may be changed without prior notice.

CR1220 Discharge Characteristics

Test condition : cotinuous discharge, Initial, 20deg.C



This is only for reference. (not guaranteed.) The information contained herein may be changed without prior notice.

CR1220 Discharge Characteristics

Test condition: $62k\Omega$ continuous discharge, Initial



Service Life (h)

RIY-]

This is only for reference. (not guaranteed.) The information contained herein may be changed without prior notice.

CR1220 Load Resistance vs Capacity

Test condition : Initial, 20 deg.C



This is only for reference. (not guaranteed.) The information contained herein may be changed without prior notice.

CR1220 Leakage Performance

	Test items	Electrolyte Leakage (%)			
Test condition	Storage period	20days	40days	60days	90days
Storage at high temperature	45deg.C-70%RH	0	0	0	0
and high humidity	60deg.C-90%RH	0	0	-	-
Temperature cycle	Temperature: -10deg.C 60deg.C (4h/Cycle, 6cycle/day)	0	-	-	-

This is only for reference.(not guaranteed.) This information contained herein may be changed without prior notice.

TOSHIBA

CR1220 Safety Evaluation Test

	n	Conditions	Requirements
Heat test	5	Cells are kept stored for 24hrs. Temperature: 80+/-2deg.C Humidity: 70%RH or less.	Open-circuit voltage is to be kept same as initial value. No abnormal appearance and no substandard dimensions are to be observed.
Vibration test	5	Amplitude: 1.0mm Frequency: 10 to 55 to 10Hz Sweep: 1minute Period: 2h per each direction of X and Y axes, 4h in total	Open-circuit voltage is to be kept same as initial value. No abnormal appearance and no substandard dimensions are to be observed.
Drop test	5	Number of drops: 10 times Height: 75cm Floor: Concrete Direction: Free	Open-circuit voltage is to be kept same as initial value. No abnormal appearance and no substandard dimensions are to be observed.
Weighing test	5	Weight of 19.8N(2kgf) is laid for 1 hour and 9.8N(1kgf) for 24 hours respectively on all over negative side of cells.	Open-circuit voltage is to be kept same as initial value. No abnormal appearance and no substandard dimensions are to be observed.
Short-circuit test	5	Cells are Short-circuited for 48 hours.	No burst, No fire



Confidential

CR1220 Outline Drawing



Unit: mm

This is only for reference.(not guaranteed.) This information contained herein may be changed without prior notice.