



Li98 Series Thermal Tape

REACH Compliant RoHS Compliant

Features

- Good adhesion
- Great reliability
- Cost effective with great performance
- Easy to assemble
- Customization services

Application:


Electronic Components - 5G, Aerospace, AI, AIoT, AR/VR/MR/XR, Automotive, Consumer Devices, Datacom, Electric Vehicle, Electronic Products, Energy Storage, Industrial, Lighting Equipment, Medical, Military, Netcom, Panel, Power Electronics, Robot, Servers, Smart Home, Telecom, etc.

Storage:

T-Global guarantees a 6-month shelf life at maximum continuous storage. Storage temperature should be under 25°C to maintain controlled adhesion to the liner.

Properties

Thermal Conductivity : 1(Li98) / 1.3(Li98T) / 1.9(Li98C) / 2.1(Li98CN) W/m•K



Properties	Unit	Li98		Li98T	Li98C		Li98CN	Tolerance	Test Method
Thermal Conductivity	W/m•K	1	1	1.3	1.9	1.9	2.1	±10%	ASTM D5470 Modified
Thickness	mm	0.15	0.25	0.11	0.15	0.25	0.18	-	ASTM D374
Color	White							-	-
Reinforcement Carrier	-	Fiberglass Mesh		PET	Fiberglass Mesh		-	-	-
Operating Temperature	° C	-30~+120		-60~+120	-30~+120			-	-
Short Time Use Temperature (30sec)	° C	200						-	-
Density	g/cm³	1.85		1.6	1.8	1.8	1.8	±5%	ASTM D792
Tensile Strength	psi	200	400	400	200	400	-	-	ASTM D412
Glass Transition Temperature	° C	-30	-30	-	-27	-27	-30	-	-
Initial Tack	cm	10	8	10	14	12	15	-	PSTC-6
Lap Shear Strength	N/cm²	61		60	55	50	55	-	ASTM D1002
Die Shear Strength@25° C	N/cm²	120		105	109	100	100	-	-
Die Shear Strength@80° C	N/cm²	69		60	68	68	55	-	-
Holding Power 1000g@25° Cusing 1 in²	min	>10000						-	PSTC-7
Holding Power 1000g@80° Cusing 1 in²	min	>10000						-	PSTC-7
Peeling Strength 90° (Aluminum)	N/in	>10	>12	>12	>6	>8	>8	-	ASTM D3330
Dielectric Breakdown Voltage (AC)	KV	≥2	≥3.1	≥4.1	≥2	≥3.1	≥5.1	-	ASTM D149
Dielectric Breakdown Voltage (DC)	KV	≥3.1	≥4.1	≥5.1	≥3.1	≥4.1	≥6.1	-	ASTM D149
Thermal Impedance@10psi	° C*in²/W	0.93	1.26	0.63	0.64	0.89	0.73	-	ASTM D5470 Modified
Thermal Impedance@30psi	° C*in²/W	0.76	1.05	0.60	0.60	0.85	0.68	-	ASTM D5470 Modified
Thermal Impedance@50psi	° C*in²/W	0.61	1.06	0.59	0.53	0.87	0.66	-	ASTM D5470 Modified

※Die-cut for different shapes

※Roll type available

T-Global Technology (Europe & North America) Ltd.

Units 1-2 Cosford Business Park, Central Park, Lutterworth, Leicestershire, LE17 4QU, United Kingdom  
T +44 (0)1455 553 510 E sales@tglobaltechnology.com W www.tglobaltechnology.com

NOTICE: The information contained herein is to the best of our knowledge true and accurate. Values stated in this technical data sheet represent typical values as not all tests are run on each lot of material produced. All specifications are subject to change without notice. The protective film and release paper does not affect the function of the product. If there is no special requirement, the default depends on T-Global. Since the varied conditions of potential use are beyond our control, all recommendations or suggestions are presented without guarantee or responsibility on our part and users should make their own test to determine the suitability of our products in any specific situation. This product is sold without warranty either expressed or implied, of fitness for a particular purpose or otherwise, except that this product shall be of standard quality, and except to the extent otherwise stated in T-Global Technology's invoice, quotation, or order acknowledgment. We disclaim any and all liabilities incurred in connection with the use of information contained herein, or otherwise. All risks of such are assumed by the user. Furthermore, nothing contained herein shall be construed as a recommendation to use any process or to manufacture or to use any product in conflict with existing or future patents covering any product or material or its use.

Version19  
20240326

