

# LOCTITE ECCOBOND FP4530SF

July 2017

## PRODUCT DESCRIPTION

LOCTITE ECCOBOND FP4530SF provides the following product characteristics:

|                             |  |
|-----------------------------|--|
| <b>Technology</b>           | Epoxy  |
| <b>Appearance</b>           | blue   |
| <b>Product Benefits</b>     | <ul style="list-style-type: none"> <li>• Snap curable</li> <li>• Compatible with small gap sizes</li> <li>• Fast flow</li> </ul> |
| <b>Filler Weight, %</b>     | 50   |
| <b>Cure</b>                 | Heat cure  |
| <b>Application</b>          | Underfill  |
| <b>Typical Applications</b> | Flip Chip  |

LOCTITE ECCOBOND FP4530SF underfill is designed for flip chip on flex applications with a 25 micron gap. This material is formulated to change color from blue to green during the cure process to indicate the cure status.

LOCTITE ECCOBOND FP4530SF is the silane-free version of LOCTITE ECCOBOND FP4530.

## TYPICAL PROPERTIES OF UNCURED MATERIAL

|  |       |
|--|-------|
| Viscosity, Brookfield - Cone & Plate, 25 °C, mPa·s (cP): |       |
| Spindle 52, speed 20 rpm                                 | 3,300 |
| Flow Rate @ 90°C, seconds:                               |       |
| @ 500 mil travel, 3 mil gap                              | 30    |
| @ 500 mil travel, 1 mil gap                              | 60    |
| Pot Life @ 25°C, hours                                   | 24    |
| Pot Life typical dispensing conditions, hours            | 8     |
| Shelf Life @ -40°C, months                               | 9     |
| Flash Point - See SDS                                    |       |

## TYPICAL CURING PERFORMANCE

### Gel Time

|                            |   |
|----------------------------|---|
| Gel Time @ 121 °C, minutes | 7 |
|----------------------------|---|

### Snap Cure Schedule

|                   |  |
|-------------------|--|
| 8 minutes @ 160°C |  |
|-------------------|--|

### Substrate Temperature

|                 |    |
|-----------------|----|
| Temperature, °C | 90 |
|-----------------|----|

The above cure profiles are guideline recommendations. Cure conditions (time and temperature) may vary based on customers' experience and their application requirements, as well as customer curing equipment, oven loading and actual oven temperatures.

## TYPICAL PROPERTIES OF CURED MATERIAL

### Physical Properties :

|  |  |
|--|--|
| Coefficient of Thermal Expansion , ppm/°C:   |  |
| Below Tg                                     | 45   |
| Above Tg                                     | 150  |
| Glass Transition Temperature (Tg) by TMA, °C | 145  |
| Extractable Ionic Content, ppm:              |  |
| Chloride (Cl-)                               | 9  |
| Sodium (Na+)                                 | 3  |
| Potassium (K+)                               | 1  |
| Flexural Modulus                             | N/mm <sup>2</sup> 5,600<br>(psi) (812,000) |

## GENERAL INFORMATION

For safe handling information on this product, consult the Safety Data Sheet, (SDS).

**This product is not recommended for use in pure oxygen and/or oxygen rich systems and should not be used with chlorine or other strong oxidizing materials.**

## THAWING:

1. Allow container to reach room temperature before use.
2. After removing from the freezer, set the syringes to stand vertically while thawing.
3. DO NOT re-freeze. Once thawed, the adhesive should not be re-frozen.

## DIRECTIONS FOR USE

1. For best flow rates, a preheat temperature of 90 °C is recommended.
2. For best results in dispensing a 21 gauge needle should be used at 10 psi pressure.

## Not for product specifications

The technical data contained herein are intended as reference only. Please contact your local quality department for assistance and recommendations on specifications for this product.

**STORAGE:**

Store product in the unopened container in a dry location. Storage information may be indicated on the product container labeling.

**Optimal Storage: -40°C. Storage below -40°C or greater than -40°C can adversely affect product properties.**

Material removed from containers may be contaminated during use. Do not return product to the original container. Henkel Corporation cannot assume responsibility for product which has been contaminated or stored under conditions other than those previously indicated. If additional information is required, please contact your local Technical Service Center or Customer Service Representative.

**Conversions**

$(^{\circ}\text{C} \times 1.8) + 32 = ^{\circ}\text{F}$   
 $\text{kV/mm} \times 25.4 = \text{V/mil}$   
 $\text{mm} / 25.4 = \text{inches}$   
 $\text{N} \times 0.225 = \text{lb}$   
 $\text{N/mm} \times 5.71 = \text{lb/in}$   
 $\text{psi} \times 145 = \text{N/mm}^2$   
 $\text{MPa} = \text{N/mm}^2$   
 $\text{N}\cdot\text{m} \times 8.851 = \text{lb}\cdot\text{in}$   
 $\text{N}\cdot\text{m} \times 0.738 = \text{lb}\cdot\text{ft}$   
 $\text{N}\cdot\text{mm} \times 0.142 = \text{oz}\cdot\text{in}$   
 $\text{mPa}\cdot\text{s} = \text{cP}$

**Disclaimer  
Note**

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. The product can have a variety of different applications as well as differing application and working conditions in your environment that are beyond our control. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product.

Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

**In case products are delivered by Henkel Belgium NV, Henkel Electronic Materials NV, Henkel Nederland BV, Henkel Technologies France SAS and Henkel France SA please additionally note the following:**

In case Henkel would be nevertheless held liable, on whatever legal ground, Henkel's liability will in no event exceed the amount of the concerned delivery.

**In case products are delivered by Henkel Colombiana S.A.S. the following disclaimer is applicable:**

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. Henkel, is therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm

such suitability of our product.

Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

**In case products are delivered by Henkel Corporation Resin Technology Group, Inc., or Henkel Canada, Inc. the following disclaimer is applicable:**

The data contained herein are furnished for information only and are believed to be reliable. We cannot assume responsibility for the results obtained by others over whose methods we have no control. It is the user's responsibility to determine suitability for the user's purpose of any production methods mentioned herein and to adopt such precautions as may be advisable for the protection of property and of persons against any hazards that may be involved in the handling and use thereof. In light of the foregoing, **Henkel Corporation specifically disclaims all warranties expressed or implied, including warranties of merchantability or fitness for a particular purpose, arising from sale or use of Henkel Corporation's products. Henkel Corporation specifically disclaims any liability for consequential or incidental damages of any kind, including lost profits.** The discussion herein of various processes or compositions is not to be interpreted as representation that they are free from domination of patents owned by others or as a license under any Henkel Corporation patents that may cover such processes or compositions. We recommend that each prospective user test his proposed application before repetitive use, using this data as a guide. This product may be covered by one or more United States or foreign patents or patent applications.

**Trademark usage**

Except as otherwise noted, all trademarks in this document are trademarks of Henkel Corporation in the U.S. and elsewhere. ® denotes a trademark registered in the U.S. Patent and Trademark Office.

Reference 1