

LOCTITE HHD 6008

October 2021

PRODUCT DESCRIPTION

LOCTITE HHD 6008 provides the following product characteristics:

Technology	Polyurethane
Appearance - Part A Polyol	Beige liquid
Appearance - Part B Iso	Beige liquid
Appearance - Mixed	White to grayish paste
Mix Ratio by volume, Part A:Part B	2 : 1
Cure	Room temperature cure after mixing, heat cure
Product Benefits	<ul style="list-style-type: none"> High shear strength High tensile strength High impact resistance
Operating Temperature Range	-30 to 80°C
Application	Structural adhesive, Electronic structural bonding
Typical Assembly Applications	Consumer electronic device assembly

LOCTITE HHD 6008 two component polyurethane adhesive is designed for fast cure and high impact resistance. This product bonds a variety of substrates exceptionally well. LOCTITE HHD 6008 reacts when mixed and is fully cured at room temperature. Cure can be accelerated with application of heat.

TYPICAL PROPERTIES OF UNCURED MATERIAL

Part A Properties (Polyol)

Specific Gravity @ 25°C, g/cm ³	1.0
Viscosity, Brookfield CP52, 25 °C, mPa·s (cP):	
Spindle 14, Speed 5 rpm	121,000

Part B Properties (Isocyanate)

Specific Gravity @ 25°C	1.24
Viscosity, Brookfield CP52, 25 °C, mPa·s (cP):	
Spindle 14, Speed 10 rpm	81,000

TYPICAL CURING PERFORMANCE

LOCTITE HHD 6008 is cured after mixing at room temperature.

Cure can be accelerated by exposure to the following heat cure conditions:

Recommended Heat Cure Schedule

60 minutes @ 45°C plus 7 days @ room temperature

Alternate Heat Cure Schedule

20 minutes @ 80°C plus 24 hours @ room temperature

The above cure profiles are guideline recommendations. Cure conditions (time and temperature) may vary based on customers' experience and specific application requirements, as well as customer curing equipment, oven loading and actual oven temperatures.

TYPICAL PROPERTIES OF CURED MATERIAL

Physical Properties

Hardness, Shore D, ISO 868	58
Glass Transition Temperature (Tg) by TMA, °C	35
Coefficient of Thermal Expansion, TMA:	
Below Tg, ppm/°C	97.5
Above Tg, ppm/°C	225.7
Elongation, ISO 527-2, %	207
Modulus of Elasticity, ISO 527-2, N/mm ²	208
Tensile Strength at break, ISO 527-2, N/mm ²	17
Storage Modulus, DMA, N/mm ²	232
Volumetric Shrinkage, %	4.8

Adhesion Properties

Lap Shear Strength, ISO 4587, 0.127 mm spacer beads:

Al to Al	N/mm ²	14.13
	(psi)	(2,050)
IXEF to IXEF	N/mm ²	6.7
	(psi)	(972)

GENERAL INFORMATION

For safe handling information on this product, consult the Safety Data Sheet, (SDS).

DIRECTIONS FOR USE

- DO NOT open foil package until the adhesive is ready to use.
- Use gloves to minimize skin contact. DO NOT use solvents for cleaning hands.
- DUAL CONTAINERS:** Material is dispensed through volumetric metered mixing equipment attached to static mix nozzles.

4. For high strength structural bonds, remove surface contaminants such as paint, oxide films, oils, dust, mold release agents and all other surface contaminants.
5. For maximum bond strength apply adhesive evenly to the surface to be bonded. Parts should be assembled immediately after adhesive has been applied.
6. Application to the substrates should be made as soon as possible. Larger quantities and/or higher temperatures will reduce the working time.
7. Join the adhesive coated surfaces and allow to cure. High temperatures will speed up curing.
8. Keep the assembled parts from moving during cure. The joint should be allowed to develop full strength before subjecting to any service loads.
9. Excessive uncured adhesive can be cleaned up with keton type solvents.

Storage

Store product in the unopened container in a dry location. Storage information may be indicated on the product container labeling.

Optimal Storage : Refer to package label for proper storage condition.

Material removed from containers may be contaminated during use. Do not return product to the original container. Henkel Corporation cannot assume responsibility for product which has been contaminated or stored under conditions other than those previously indicated. If additional information is required, please contact your local Henkel Representative.

Conversions

$(^{\circ}\text{C} \times 1.8) + 32 = ^{\circ}\text{F}$
 $\text{kV/mm} \times 25.4 = \text{V/mil}$
 $\text{mm} / 25.4 = \text{inches}$
 $\text{N} \times 0.225 = \text{lb/F}$
 $\text{N/mm} \times 5.71 = \text{lb/in}$
 $\text{psi} \times 145 = \text{N/mm}^2$
 $\text{MPa} = \text{N/mm}^2$
 $\text{N}\cdot\text{m} \times 8.851 = \text{lb}\cdot\text{in}$
 $\text{N}\cdot\text{m} \times 0.738 = \text{lb}\cdot\text{ft}$
 $\text{N}\cdot\text{mm} \times 0.142 = \text{oz}\cdot\text{in}$
 $\text{mPa}\cdot\text{s} = \text{cP}$

Not for product specifications

The technical data contained herein are intended as reference only. Please contact your local Henkel representative for assistance and recommendations on the specifications of this product.

Disclaimer

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. The product can have a variety of different applications as well as differing application and working conditions in your environment that are beyond our control. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product. Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

In case products are delivered by Henkel Belgium NV, Henkel Electronic Materials NV, Henkel Nederland BV, Henkel Technologies France SAS and Henkel France SA please additionally note the following:

In case Henkel would be nevertheless held liable, on whatever legal ground, Henkel's liability will in no event exceed the amount of the concerned delivery.

In case products are delivered by Henkel Colombiana, S.A.S. the following disclaimer is applicable:

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product.

Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

In case products are delivered by Henkel Corporation, or Henkel Canada Corporation, the following disclaimer is applicable:

The data contained herein are furnished for information only and are believed to be reliable. We cannot assume responsibility for the results obtained by others over whose methods we have no control. It is the user's responsibility to determine suitability for the user's purpose of any production methods mentioned herein and to adopt such precautions as may be advisable for the protection of property and of persons against any hazards that may be involved in the handling and use thereof. In light of the foregoing, **Henkel Corporation specifically disclaims all warranties expressed or implied, including warranties of merchantability or fitness for a particular purpose, arising from sale or use of Henkel Corporation's products. Henkel Corporation specifically disclaims any liability for consequential or incidental damages of any kind, including lost profits.** The discussion herein of various processes or compositions is not to be interpreted as representation that they are free from domination of patents owned by others or as a license under any Henkel Corporation patents that may cover such processes or compositions. We recommend that each prospective user test his proposed application before repetitive use, using this data as a guide. This product may be covered by one or more United States or foreign patents or patent applications.

Trademark usage

Except as otherwise noted, all trademarks in this document are trademarks of Henkel Corporation in the U.S. and elsewhere. ® denotes a trademark registered in the U.S. Patent and Trademark Office.

Reference 1