

LOCTITE STYCAST US 0146

February 2019

PRODUCT DESCRIPTION

LOCTITE STYCAST US 0146 provides the following product characteristics:

Technology	Polyurethane
Appearance,Resin (Component A)	Amber
Appearance, Hardener (Component B)	Amber
Appearance (cured)	Amber
Components	Two components - requires mixing
Mixing Ratio, by weight Component A: Component B	100 : 100
Mix Ratio by volume: Part A: Part B	100 : 110
Product Benefits	Unfilled
	Low viscosity
	Low durometer
	Long pot life
	Hydrolytic stability
Cure	Room Temperature or Heat Cure
Application	Potting

LOCTITE STYCAST US 0146 is a casting system formulated for potting.

TYPICAL PROPERTIES OF UNCURED MATERIAL Part & Properties

Viscosity, Brookfield - RVF, 25 °C, mPa·s (cP):	
Spindle 2, speed 20 rpm	40
Specific Gravity, @ 25°C, gm/cc	1.07
Part B Properties	
Viscosity, Brookfield - RVF, 25 °C, mPa·s (cP):	
Spindle 2, speed 20 rpm	940
Density @ 25°C, gm/cc	1.07
Mixed Properties	
Viscosity, Brookfield - RVF, 25 °C, mPa·s (cP): Spindle 2, speed 20 rpm	205

TYPICAL CURING PERFORMANCE Recommended Cure

4 to 5 hours @ 85°C

Alternative Cure Schedule

24 to 28 hours (7 days for full cure)

The above cure profiles are guideline recommendations. Cure conditions (time and temperature) may vary based on customers' experience and their application requirements, as well as customer curing equipment, oven loading and actual oven temperatures.

TYPICAL PROPERTIES OF CURED MATERIAL

Physical Properties :

Coefficient of Thermal Expansion. ppm/°C:			
Below Tg (-40 to -30°C)		47	
Above Tg (40 to 80° C)		230	
Glass Transition Temperature (Tg) °C -21.3		1.3	
Coefficient of Thermal Conductivity, W/(m-K)	0.	2	
Shore Hardness, Durometer A		50	
Tensile Strength	N/mm² (psi)	1.3 (185)	
Tensile Modulus	N/mm² (psi)	1.3 (195)	
Water Absorption wt., %:			
24 hour immersion		0.11	
7 day immersion 0.14		14	
Heat Aging, 168 hours @ 100°C:			
Hardness Gain		4	
Weight loss, %	0.53		
Hydrolytic Stability (7 days boiling water):			
Hardness Loss	7		
Weight Gain, %	0.63		
Elongation ,%	14	40	
Electrical Properties:			
Dielectric Strength 0.02 in thickness, volts/mil	1,	175	
Dielectric Constant / Dissipation Factor: @ 23 °C:			
1 kHz		.84 / 0.171	
10 kHz		.06 / 0.176	
@ 85 °C:			
1kHz	6	.45 / 0.26	
10 kHz	6	.38 / 0.015	
Volume Resistivity, ohms-cm:			
@ 23 °C	4.	2×10 ¹³	
@ 85 °C		4×10 ¹²	
Surface Resistivity, ohms:			
@ 23 °C		1×10 ¹⁴	
@ 85 °C		.3×10 ¹²	

GENERAL INFORMATION

For safe handling information on this product, consult the Safety Data Sheet, (SDS).

Not for product specifications

The technical data contained herein are intended as reference only. Please contact your local quality department for assistance and recommendations on specifications for this product.



DIRECTIONS FOR USE

- Storage of LOCTITE STYCAST US 0146 Part A at too low a temperature, even for short periods of time, can result in the formation of solid MDI crystals, which occurs at approximately 15°C. This crystallization should be reversed during the curing of LOCTITE STYCAST US 0146 at 85°C.
- If desired, crystallization can be removed from LOCTITE STYCAST US 0146 Part A by heating to 60°C for approximatively 4 hours (or until crystallization is removed) with stirring and inspection every hour. LOCTITE STYCAST US 0146 Part A can be stirred either by drum rolling or mixing and resealing the drum with a nitrogen purge.
- Do not heat the drum of LOCTITE STYCAST US 0146 Part A to 70°C, as prolonged exposure to temperatures in excess of 70°C may cause dangerous pressure build-up, resulting in the deformation and/or rupture of sealed containers.
- 4. To prevent excessive local over-heating, avoid the use of electrical heat tape and open flames when heating this product.

STORAGE:

Store product in the unopened container in a dry location. Storage information may be indicated on the product container labeling.

Liquid Storage - Liquids should be stored at 25°C or below, in closed containers. If stored below 25°C, the material MUST be allowed to come to room temperature, in the sealed container, to avoid moisture contamination.

Material removed from containers may be contaminated during use. Do not return product to the original container. Henkel Corporation cannot assume responsibility for product which has been contaminated or stored under conditions other than those previously indicated. If additional information is required, please contact your local Technical Service Center or Customer Service Representative.

Conversions

 $(^{\circ}C \ge 1.8) + 32 = ^{\circ}F$ kV/mm $\ge 25.4 =$ V/mil mm / 25.4 = inches N $\ge 0.225 =$ lb N/mm $\ge 5.71 =$ lb/in psi $\ge 145 =$ N/mm² MPa = N/mm² N·m $\ge 8.851 =$ lb·in N·m $\ge 0.738 =$ lb·ft N·mm $\ge 0.738 =$ lb·ft N·mm $\ge 0.142 =$ oz·in mPa·s = cP

Disclaimer

Note:

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. The product can have a variety of different applications as well as differing application and working conditions in your environment that are beyond our control. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product.

Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

In case products are delivered by Henkel Belgium NV, Henkel Electronic Materials NV, Henkel Nederland BV, Henkel Technologies France SAS and Henkel France SA please additionally note the following:

In case Henkel would be nevertheless held liable, on whatever legal ground, Henkel's liability will in no event exceed the amount of the concerned delivery.

In case products are delivered by Henkel Colombiana, S.A.S. the following disclaimer is applicable:

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product.

Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

In case products are delivered by Henkel Corporation, Resin Technology Group, Inc., or Henkel Canada Corporation, the following disclaimer is applicable:

The data contained herein are furnished for information only and are believed to be reliable. We cannot assume responsibility for the results obtained by others over whose methods we have no control. It is the user's responsibility to determine suitability for the user's purpose of any production methods mentioned herein and to adopt such precautions as may be advisable for the protection of property and of persons against any hazards that may be involved in the handling and use thereof. In light of the foregoing, Henkel Corporation specifically disclaims all warranties expressed or implied, including warranties of merchantability or fitness for a particular purpose, arising from sale or use of Henkel Corporation's products. Henkel Corporation specifically disclaims any liability for consequential or incidental damages of any kind, including lost profits. The discussion herein of various processes or compositions is not to be interpreted as representation that they are free from domination of patents owned by others or as a license under any Henkel Corporation patents that may cover such processes or compositions. We recommend that each prospective user test his proposed application before repetitive use, using this data as a guide. This product may be covered by one or more United States or foreign patents or patent applications.

Trademark usage: [Except as otherwise noted] All trademarks in this document are trademarks and/or registered trademarks of Henkel and its affiliates in the U.S. and elsewhere.

Reference N/A