

High Temperature Rigid Urethane

8820 is a black, tough, high temperature, two-part polyurethane potting compound. It has a low mixed viscosity and properties similar to epoxy compounds, but with exceptional low temperature stability. As well, it adheres strongly to a wide variety of substrates, including metals, composites, glass, ceramics, and many plastics.

8820 offers exceptional physical protection, a high continuous operating temperature, and superior protection from acids, bases, and many organic solvents.

Features & Benefits

- 2:1 mix ratio
- 15 minute working time
- 48 hour cure at room temperature
- Constant service temperature of -50 to 150 °C
- Low exotherm
- Excellent dielectric properties

Cure Instructions

Allow to cure at room temperature for 48 hours, or cure in an oven at one of these time/temperature options:

Temperature	65 °C	80 °C
Time	2 h	1.5 h

Moisture contamination can create large bubbles and a lumpy appearance. For consistent curing results, ensure that part A is dry before use and the mixture is kept dry during cure. If moisture contamination of part A is suspected, follow the steps below:

1. Pre-heat part A at 65 °C for 2 hours. Mix the heated resin with the appropriate amount of hardener (do not allow the resin to cool as this may create condensation that wets the resin).
2. Mix the 2 components together and cure in an enclosure that has a constant stream of nitrogen gas flowing through to keep the environment dry.



Available Packaging

Part #	Packaging	Net Vol.	Net Wt.
8820-2.55L	3 Can kit	2.55 L	3 kg
8820-10.8L	3 Can kit	10.8 L	12.7 kg
8820-60L	3 Pail kit	60 L	70.6 kg

Storage and Handling

Store between 16 and 27 °C in a dry area, away from sunlight (see SDS). Minimize the time that the container is kept opened and purge with nitrogen before closing if the material is not used up at once.

Liquid Properties

Chemistry	Polyurethane	—
Density	1.2 g/mL (Mixed) 1.2 g/mL (A) 1.2 g/mL (B)	ASTM D1475
Viscosity @ 25 °C	3 820cP (Mixed) 10 700 cP (A) 250 cP (B)	Brookfield Engineering labs Inc. IPCTM-65- Method 2.4.24.4
Mix Ratio	2:1 (Volume) 1.85:1 (Weight)	—
Working Time ^a	15 min	—
Shrinkage	5.7%	Calculated
Shelf Life	2 y	—

^aBased on 100 g sample. Varies by volume and geometry.

Cured Properties

Flame Retardancy	No	—
Color	Black	—
Density	1.2 g/mL	Hydrostatic Weighing
Service Temperature Range	-50–150 °C	—
Intermittent Temperature	175 °C	—
Thermal Conductivity @ 25 °C	0.3 W/(m·K)	ASTM E1461
Specific Heat Capacity @ 25 °C	1.4 J/(g·K)	
Thermal Diffusivity @ 25 °C	0.2 mm ² /s	
Glass Transition Temperature (T _g)	44 °C	ASTM E1545
Coefficient of Thermal Expansion (CTE)	94 ppm/°C (Prior T _g) 195 ppm/°C (After T _g)	ASTM E831
Hardness	73 D	ASTM D2240
Tensile Strength	38 N/mm ²	ASTM D638
Compressive Strength	295 N/mm ²	ASTM D695

Lap Shear	13 N/mm ² (Stainless Steel) 12 N/mm ² (Aluminum) 3.7 N/mm ² (ABS) 4.9 N/mm ² (PC)	ASTM D1002
Resistivity	1.4 x 10 ¹³ Ω·cm	ASTM D257
Breakdown Voltage @ 3.175 mm	47 300 V	ASTM D149
Dielectric Strength @ 3.175 mm	480 V/mil	
Chemical Absorption	1 % (IPA)	—
Weight Gain, 30 days @ 25 °C	12 % (Toluene) 0.7 % (Sulphuric Acid 3%) 0.5 % (Acetic Acid) 0.3 % (10% NaOH) 0.3 % (10% NaCl) 0.4 % (Water) 0 % (Transmission Oil) 0 % (Transformer Oil) 0.4 % (Gasoline)	
Water Absorption ^b @ 1 week	0.1% (water), 0.05% (10% salt water)	—
@ 2 weeks	0.4% (water), 0.2% (10% salt water)	
@ 4 weeks	0.7% (water), 0.5% (10% salt water)	

MG Chemicals 1210 Corporate Drive Burlington, Ontario, Canada L7L 5R6 ISO 9001:2015 Quality Management System SAI Global File: 004008
support@mgchemicals.com **North America** +(1) 800-340-0772 **International** +(1) 905-331-1396 **Europe** +44 1663 362888 **24 March 2025 / Ver. 5.0**

Application Instructions

Read the product SDS and Application Guide for more detailed instructions before using this product.

Recommended Preparation

Clean the substrate with 824 99.9% Isopropyl Alcohol, so the surface is free of oils, dust, and other residues.

Mixing

1. (Optional) Pre-heat part A to improve surface quality.
2. Scrape settled material free from the bottom and sides of the part A container; stir the contents until homogenous.
3. Measure 2 parts by volume of the pre-stirred part A, and pour into the mixing container. Ensure all contents are transferred by scraping the container.
4. Measure 1 part by volume of the part B, and pour into the mixing container. Ensure all contents are transferred by scraping the container.
5. Thoroughly mix parts A and B together.
6. (Optional) Put in a vacuum chamber at 25 inHg.
7. Pour the mixture into a container holding the components to be protected.
8. Blanket both parts with nitrogen if the material is not used up to prevent moisture.
9. Close the part A and B containers tightly between uses.

Mixing >500 g at a time decreases working time and can lead to a flash cure. Limit the size of hand-mixed batches. For large production volumes, contact MG Chemicals Technical Support for assistance.

Disclaimer: This information is believed to be accurate. It is intended for professional end-users who have the skills required to evaluate and use the data properly. M.G. Chemicals Ltd. does not guarantee the accuracy of the data and assumes no liability in connection with damages incurred while using it.