




0058868A9

110 Delta Drive
Pittsburgh, PA 15238
NAFTA Sales: (1)800-245-3984
HK Sales : (852)3102-9337
magnetics@spang.com
www.mag-inc.com



High Flux Permeability (μ)	A_L (nH/T ²)	Core Marking			Coating Color
		Lot Number	Part Number	Inductance Grade	
26	30 $\pm$ 8%	XXXXXX	58868A9	N/A	Khaki

Dimensions	Uncoated		Coated Limits			Packaging Cardboard cut-outs Box Qty= 45 pcs
	(mm)	(in)	(mm)	(in)		
OD (A)	77.80	3.063	79.33	3.123	max	
ID (B)	49.23	1.938	47.82	1.883	min	
HT (C)	12.70	0.500	14.28	0.562	max	

Electrical Characteristics			Physical Characteristics						
Watt Loss @ 100 kHz, 100mT max (mW/cm ³)	DC Bias min (oersteds)		Voltage Breakdown wire to wire min (V _{AC})	Break Strength min (kg)	Window Area W _A (mm ²)	Cross Section A _e (mm ²)	Path Length L _e (mm)	Volume V _e (mm ³)	Weight (g)
1250	80%	50%	8000	141.0	1,820	176	196	34,500	240
	200	375							

Winding Information						Temperature Rating		
Winding Length Per Turn				Wound Coil Dimensions (mm)			Curie Temp: 460°C	
Winding Factor	(mm)	Winding Factor	(mm)	40% Winding Factor	OD	86.6	Coating Temp (Continuous up to): 200°C	
					HT	29.1		
				Completely Full Window	Max OD	112		Notes:
					Max HT	54.3		
0%	58.4	40%	83.5	Surface Area (mm²)				
20%	70.9	45%	86.7					
25%	74.1	50%	90.4					
30%	76.3	60%	98.1	Unwound Core		11,000		
35%	80.4	70%	107	40% Winding Factor		23,000		

Typical DC Bias Performance

