




0059894A2S01

110 Delta Drive
Pittsburgh, PA 15238
NAFTA Sales: (1)800-245-3984
HK Sales : (852)3102-9337
magnetics@spang.com
www.mag-inc.com



High Bias Edge Permeability (μ)	A_L (nH/T ²)	Core Marking			Coating Color
		Lot Number	Part Number	Inductance Grade	
60	75 $\pm$ 8%	XXXXXX	59894A2S01	N/A	Green

Dimensions	Uncoated		Coated Limits			Packaging Cardboard cut-outs Box Qty= 400 pcs
	(mm)	(in)	(mm)	(in)		
OD (A)	26.92	1.060	27.69	1.090	max	
ID (B)	14.73	0.580	14.10	0.555	min	
HT (C)	11.18	0.440	11.94	0.470	max	

Electrical Characteristics			Physical Characteristics						
Watt Loss @ 100kHz, 100mT max (mW/cm ³)	DC Bias min (oersteds)		Voltage Breakdown wire to wire min (V _{AC})	Break Strength min (kg)	Window Area W _a (mm ²)	Cross Section A _e (mm ²)	Path Length L _e (mm)	Volume V _e (mm ³)	Weight (g)
700	80%	50%	3000	77.0	156	65.4	63.5	4,150	35.5
	130	200							

Winding Information						Temperature Rating	
Winding Length Per Turn				Wound Coil Dimensions (mm)			Curie Temp: 500°C
Winding Factor	(mm)	Winding Factor	(mm)	40% Winding Factor	OD	30.9	Coating Temp (Continuous up to): 200°C
					HT	16.7	
				Completely Full Window	Max OD	30.9	Notes:
					Max HT	21.5	
				0%	37.5	40%	
20%	41.1	45%	45.6				
25%	42.1	50%	46.8				
30%	42.8	60%	49.0 <th colspan="2">Unwound Core</th> <td>2,500</td>	Unwound Core		2,500	
35%	43.8	70%	51.4 <th colspan="2">40% Winding Factor</th> <td>3,500</td>	40% Winding Factor		3,500	

Typical DC Bias Performance

