




0077141A7

110 Delta Drive
Pittsburgh, PA 15238
NAFTA Sales: (1)800-245-3984
HK Sales : (852)3102-9337
magnetics@spang.com
www.mag-inc.com



Kool Mμ Permeability (μ)	A _L (nH/T ²)	Core Marking			Coating Color
		Lot Number	Part Number	Inductance Grade	
60	13 ± 15%	N/A	N/A	N/A	Black

Dimensions	Uncoated		Coated Limits			Packaging Bulk Pack 5 vials/box Box Qty= 7500 pcs
	(mm)	(in)	(mm)	(in)		
OD (A)	3.56	0.140	4.19	0.165	max	
ID (B)	1.78	0.070	1.27	0.050	min	
HT (C)	1.52	0.060	2.16	0.085	max	

Electrical Characteristics			Physical Characteristics						
Watt Loss @ 100 kHz, 100mT max(mW/cm³)	DC Bias min (oersteds)		Voltage Breakdown wire to wire min (V _{AC})	Break Strength min (kg)	Window Area W _A (mm²)	Cross Section A _e (mm²)	Path Length L _e (mm)	Volume V _e (mm³)	Weight (g)
750	80%	50%	*-	1.8	1.27	1.30	8.06	10.5	0.0611
	39.0	87.0							

Winding Information						Temperature Rating	
Winding Length Per Turn				Wound Coil Dimensions (mm)			Curie Temp: 500°C
Winding Factor	(mm)	Winding Factor	(mm)	40% Winding Factor	OD	4.30	Coating Temp (Continuous up to): 200°C
					HT	2.56	
				Completely Full Window	Max OD	4.95	Notes:
Max HT	2.74						
0%	7.24	40%	7.89	Surface Area (mm²)			*No voltage breakdown min for A2 or A7 with OD ≤4.65mm.
20%	7.56	45%	7.98				
25%	7.65	50%	8.08				
30%	7.70	60%	8.27	Unwound Core		60	
35%	7.81	70%	8.48	40% Winding Factor		70	

Typical DC Bias Performance

