




EQH4128E026L120

110 Delta Drive
Pittsburgh, PA 15238
NAFTA Sales: (1)800-245-3984
HK Sales : (852)3102-9337
magnetics@spang.com
www.mag-inc.com



High Flux Permeability (μ)	A_L (nH/T ²)	Core Marking	
		Lot Number	Part Number
26	94 $\pm$ 8%	XXXXXX	EQH4128E026L120


	Dimensions		Tolerance ($\pm$)			Packaging
	(mm)	(in)	(mm)	(in)		
A	41.50	1.634	0.40	0.016		Est. Box Qty = 140 Pcs
B	12.00	0.472	0.20	0.008		
C	28.00	1.102	0.30	0.012		
D	7.50	0.295	0.20	0.008		Available Hardware
E	36.50	1.437	0.30	0.012		
F	14.90	0.587	0.20	0.008		
G	26.60	1.047	0.30	0.012		

Electrical Characteristics			Physical Characteristics					
Watt Loss @ 100 kHz, 100mT max (mW/cm ³)	DC Bias min (oersteds)		Break Strength min (kg)	Window Area W_a (mm ²)	Cross Section A_e (mm ²)	Path Length L_e (mm)	Volume V_e (mm ³)	Est. Weight (Ea. Piece) (g)
850	80%	50%	56	162	200	83.6	16,700	53
	190	320						

Note: Standard A_L is controlled with full window high turns test coils. Application coils with few turns often result in lower inductance than expected, or sometimes higher.

Notes:	Temperature Rating
	Curie Temp: 500 °C

Typical DC Bias Performance



Revision 7/31/2024