



PRODUCT DATA SHEET

CORE – P2616

Appearance & Shape: To be free from any defect such as flow, burrs, unevenness etc; as per IEC standards

Effective parameters irrespective of material grade (per set)


Parameter	Value	Unit
Effective Length (L_e)	37.2	mm
Effective Area (A_e)	93.0	mm ²
Effective Area (A_{Min})	93.0	mm ²
Effective Volume (V_e)	3460	mm ³
Approx. Weight (without gap)	21.6	g/set



P2616 Un-gapped (OL)

Test Conditions: 1kHz/1mT/CFR COIL,N=100/25°C

Material Grade	Initial Permeability (μ_{iac})	AL Value (nH)/Set	P_v (W/set)	Ordering code
CF292	1800 $\pm$ 20%	4800 +30%/-20%	$\leq 0.41(100\text{mT}, 100\text{kHz}, 100^\circ\text{C})$	CF292 P2616 OL
CF139	2100 $\pm$ 20%	5300 +30%/-20%	$\leq 0.35(100\text{mT}, 100\text{kHz}, 100^\circ\text{C})$	CF139 P2616 OL
CF297	2300 $\pm$ 20%	5600 +30%/-20%	$\leq 0.31(100\text{mT}, 100\text{kHz}, 100^\circ\text{C})$	CF297 P2616 OL
CF124	2500 $\pm$ 20%	6000 +30%/-20%	$\leq 0.52(200\text{mT}, 25\text{kHz}, 100^\circ\text{C})$	CF124 P2616 OL



Remarks: Value of "G" is Zero (0) for Un-Gapped Cores, for Gapped Cores the value of "G" varies as per the Gap/AL value

For general terms and conditions please visit

http://www.cosmoferrites.com/Downloads/Downloads/bcb70e7c-ae33-40ec-a881-0d5120db57b6_GTC.pdf

Regd. Office & Works: Jabli, Distt. Solan, Himachal Pradesh – 173 209 (India)

E-mail: sales@cosmoferrites.com