FERROXCUBE

DATA SHEET

E100/60/28 E cores and accessories

New data 2008 Sep 01




E cores and accessories

CORE SETS

Effective core parameters

SYMBOL	PARAMETER VAI		UNIT
Σ(I/A)	core factor (C1)	ore factor (C1) 0.371 mm ⁻	
V _e	effective volume 202 000 mm		mm ³
l _e	effective length	274	mm
A _e	effective area	738	mm ²
A _{min}	minimum area	692	mm ²
m	mass of core half	≈ 493	g



Core halves

 A_L measured in combination with a non-gapped core half, clamping force for A_L measurements 110 \pm 30 N, unless stated otherwise.

GRADE	A _L (nH)	$\mu_{\mathbf{e}}$	AIR GAP (μm)	TYPE NUMBER
3C90	7100 ± 25 %	≈ 2100	≈ 0	E100/60/28-3C90
3C92 des	$4800\pm25~\%$	≈ 1420	≈ 0	E100/60/28-3C92
3C94	7100 ± 25 %	≈ 2100	≈ 0	E100/60/28-3C94
3C95 des	9010 ± 25 %	≈ 2665	≈ 0	E100/60/28-3C95

Properties of core sets under power conditions

	B (mT) at	CORE LOSS (W) at			
GRADE	H = 250 A/m; f = 25 kHz; T = 100 °C	f = 25 kHz; B = 200 mT; T = 100 °C	f = 100 kHz; B = 100 mT; T = 100 °C	f = 100 kHz; B = 200 mT; T = 25 °C	f = 100 kHz; B = 200 mT; T = 100 °C
3C90	≥ 320	≤ 34	≤ 34	_	_
3C92	≥ 370	_	≤ 27	_	_
3C94	≥ 320	_	≤ 27	_	_
3C95	≥ 320	_	_	≤ 145	≤ 137

2008 Sep 01 2

E cores and accessories

E100/60/28

DATA SHEET STATUS DEFINITIONS

DATA SHEET STATUS	PRODUCT STATUS	DEFINITIONS
Preliminary specification	Development	This data sheet contains preliminary data. Ferroxcube reserves the right to make changes at any time without notice in order to improve design and supply the best possible product.
Product specification	Production	This data sheet contains final specifications. Ferroxcube reserves the right to make changes at any time without notice in order to improve design and supply the best possible product.

DISCLAIMER

Life support applications — These products are not designed for use in life support appliances, devices, or systems where malfunction of these products can reasonably be expected to result in personal injury. Ferroxcube customers using or selling these products for use in such applications do so at their own risk and agree to fully indemnify Ferroxcube for any damages resulting from such application.

PRODUCT STATUS DEFINITIONS

STATUS	INDICATION	DEFINITION
Prototype	prot	These are products that have been made as development samples for the purposes of technical evaluation only. The data for these types is provisional and is subject to change.
Design-in	des	These products are recommended for new designs.
Preferred		These products are recommended for use in current designs and are available via our sales channels.
Support	sup	These products are not recommended for new designs and may not be available through all of our sales channels. Customers are advised to check for availability.

2008 Sep 01 3