

Technical Data Sheet

Inkjet Printable Polyester Film

This specification is intended to outline the physical and chemical properties of *PANDUIT*'s pressure sensitive inkjet printable polyester material with a permanent adhesive and include the following printable material identifiers:

Printable Material Part Number		
C***X***XJI	T***X***XJI	

PRODUCT SPECIFICATIONS:

Description:	Material is a RoHS compliant (European Union directive 2011/65/EU). Material is a top coated polyester film with a pressure sensitive permanent adhesive.
Print Methods:	This material is recommended for ink jet printing.
Adhesive:	Rubber based pressure sensitive permanent adhesive.
Standard Colors:	White
Thickness:	4.2 +/- 0.5 mils (substrate and adhesive)
Recommended Inks:	Pigment based inkjet ink such as Epson DURABrite Ultra®
Service Temperature Range:	-65°F to 225°F (-54°C to 107°C)
Minimum Application Temperature:	50°F(10°C)
Storage Conditions:	Store at 70°F (21°C) and 50% Relative Humidity.

PROPERTIES:**PERFORMANCE:**

Peel Adhesion to: Stainless Steel:	45 oz./in (PSTC-101, 15 min dwell) 50 oz./in (PSTC-101, 24 hour dwell)
ABS:	45 oz./in (PSTC-101, 15 min dwell) 50 oz./in (PSTC-101, 24 hour dwell)
Powder coated surface:	45 oz./in (PSTC-101, 15 min dwell) 50 oz./in (PSTC-101, 24 hour dwell)
Polypropylene:	40 oz./in (PSTC-101, 15 min dwell) 45 oz./in (PSTC-101, 24 hour dwell)
PVC:	40 oz/in (PSTC-101, 15 min dwell) 45 oz/in (PSTC-101, 24 hour dwell)
Shear Adhesion:	24 hours minimum (PSTC-107, modified procedure A)

Technical Data Sheet

Tensile Strength:	MD 40 +/- 4.0 lbs./inch width (PSTC-131) TD 55 +/- 5.5 lbs./inch width (PSTC-131)
Elongation:	MD 200% +/- 15% (PSTC-131) TD 150% +/- 15% (PSTC-131)
UV Resistance:	*3000 hours no change observed (ASTM G154)
Elevated Temperature Exposure:	After 8 hours at 250°F(121°C) there was no deterioration of the substrate
Long Term High Service Temperature:	30 days at 225°F (107°C). Slight discoloration observed 30 days at 250°F (121°C). Moderate discoloration observed.
Long Term Low Service Temperature:	30 days at -65F (-54C). No visible change observed.
Humidity Resistance:	30 days at 100F (37C) and 95% RH. No visible change observed.
Abrasion Resistance:	Taber abraser, CS-10 wheels/250 gm. wt./500 cycles, no visible change observed (ASTM D4060).
Salt Water Resistance:	90 days in 10% salt water solution at 150F. No visible change observed.
*3000 hours equate to 5 years of assimilated outdoor UV exposure.	

CHEMICAL/SOLVENT RESISTANCE:

Samples were printed with Epson DURABrite Ultra® inkjet ink and were conditioned 24 hours before testing. Testing was conducted at room temperature. The samples were immersed in the specified solvents for 5 immersions using the following cycle: a 10 minute immersion followed by a 30 minute recovery time. After the final immersion, the samples were removed from the test solvent and were rubbed 10 times with lint free gauze. Visual observations were noted for any smear or loss of legibility.

Chemical/Solvent	Visual Observation	
	Adhesive	Inkjet print after rub test
Distilled water	No effect	No effect
Mineral Spirits	No effect	No effect
Toluene	Slight adhesive bleed	Loss of print legibility
Isopropyl Alcohol	No effect	No effect
Methanol	No effect	No effect
Hydraulic fluid fire resistant	No effect	No effect
Acetone	Slight adhesive bleed	Loss of print legibility
Methyl Ethyl Ketone	Slight adhesive bleed	Loss of print legibility
1,1,1-Trichloroethane	No effect	Loss of print legibility
Freon TF	No effect	No effect
Super Agitene	No effect	No effect
Jet A Fuel	No effect	No effect
SAE 20 Motor oil	No effect	No effect
Skydrol	No effect	Loss of print legibility
Brake fluid	No effect	Loss of print legibility
Gasoline	No effect	No effect
Mil 5606 oil	No effect	No effect
10% Sodium Hydroxide	No effect	Loss of print legibility
10% Sulfuric acid	No effect	Loss of print density
10% Ammonia	No effect	No effect
3% Alconox	No effect	No effect
Simple Green	No effect	Loss of print density
Diesel Fuel	No effect	No effect
Formula 409	No effect	Loss of print density
Chlorox	No effect	Loss of print density



18900 Panduit Drive
Tinley Park, IL 60487
Customer Service: 800-777-3300

TDS:
Effective Date:
Revision:

GMY10-R
15JAN2020
0

Technical Data Sheet

APPROVALS

UL Recognized: UL969

File number: MH 14979

CUL Recognized: C22.2 No 0.15-01

File number: MH 14979

LIMITED WARRANTY

All *PANDUIT* Identification Solution Products (except for Software programs) are warranted to be free from defects in material and workmanship at the time of sale but our obligation under this warranty is limited to replacement of the product proved to be defective within 6 months from the date of sale, or in the case of printers, within 90 days from the date of sale. This warranty is void if the products or printers are modified, altered or misused in any way. Use of *PANDUIT* printers with any product other than the specified *PANDUIT* products for which the printer was designed constitutes misuse. Before using, the user shall determine the suitability of the product for its intended use and user assumes all risk and liability whatsoever in connection therewith. The foregoing may not be altered except by an agreement signed by officers of seller and manufacturer.

NEITHER *PANDUIT* NOR SELLER SHALL BE LIABLE FOR ANY OTHER INJURY, LOSS OR DAMAGE, WHETHER DIRECT OR CONSEQUENTIAL, ARISING OUT OF THE USE OF, OR THE INABILITY TO USE THE PRODUCT OR THE PRINTER.

THIS WARRANTY IS MADE IN LIEU OF AND EXCLUDES ALL OTHER WARRANTIES, EXPRESS OR IMPLIED. THE IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS OF PARTICULAR USE ARE SPECIFICALLY EXCLUDED.

The information contained in this literature is based on our experience to date and is believed to be reliable. It is intended as a guide or use by persons having technical skill at their own discretion and risk. We do not guarantee favorable results or assume any liability in connection with its use. Dimensions contained herein are for reference purposes only. This publication is not to be taken as a license to operate under, or a recommendation to infringe any existing patents. This supersedes and voids all previous literature, etc.