

BRADY B-816 STANDARD DIRECT THERMAL REMOVABLE PAPER

TDS No. B-816 Effective Date: 01/25/2019

Description: Print Technology: Direct Thermal Material Type: Paper Finish: Matte Adhesive: Removable Acrylic

APPLICATIONS

General purpose labeling applications requiring a ribbonless, low cost label material. Not recommended for high heat/humidity or outdoor applications.

REGULATORY APPROVALS

For information on the Weee-RoHS compliance status for a Brady Product go to one of the following websites:

In Canada: www.bradycanada.ca/weee-rohs

In Europe: www.bradyeurope.com/rohs

In Japan: www.brady.co.jp/products/labelsuse/rohs

All other regions: www.bradvid.com/weee-rohs

Details:

PHYSICAL PROPERTIES	TEST METHODS	AVERAGE RESULTS
Thickness	ASTM D 1000	
	Total (excluding liner)	0.004 inch (0.1 mm)
Adhesion to:	ASTM D 1000	
-Stainless Steel	20 minute dwell	21 oz/in (23 N/100 mm)
-ABS	24 hour dwell	29 oz/in (32 N/100 mm)
	20 minute dwell	17 oz/in (19 N/100 mm)
-Powder Coated Paint	24 hour dwell	29 oz/in (32 N/100 mm)
	20 minute dwell	1.3 oz/in (1.4 N/100 mm)
-Glass	24 hour dwell	0.4 oz/in (0.4 N/100 mm)
	20 minute dwell	22 oz/in (24 N/100 mm)
	24 hour dwell	26 oz/in (29 N/100 mm)
Tack	ASTM D 2979	
	Polyken™ Probe Tack	11 oz (318 g)
	0.5 second dwell	

Performance properties were tested on B-816 printed with a direct thermal printer. Printed samples were laminated to aluminum and allowed to dwell 24 hours before exposure to the indicated environments.

PERFORMANCE PROPERTIES	TEST METHOD	TYPICAL RESULTS
Long Term High Service Temperature	30 days at 140°F (60°C)	Slight discoloration to label,
		moderate discoloration around
		edges
		Print still legible
Long Term Low Service	30 days at -40°F (-40°C)	No visible effect to label or print
Temperature		
Humidity Resistance	30 days at 100°F (37°C) and 95%	Slight discoloration to label and
	R.H.	slight fade to print
Abrasion Resistance	Taber Abraser,	
	CS-10 grinding wheels, 250 g/arm,	Moderate effect to label
	100 cycles	Print still legible
	(Fed. Std. 191A, Method 5306)	-

Shelf Life:

Shelf life is two years from the date of receipt for this product as long as this product is stored in its original packaging in an environment below 80°F (27°C) and 60% RH. It remains the responsibility of the user to assess the risk of using this product. We encourage customers to develop testing protocols that will qualify a product's fitness for use in their actual application.

Trademarks:

ASTM: American Society for Testing and Materials (U.S.A.) BradyPrinter™ is a trademark of Brady Worldwide, Inc. Polyken™ is a trademark of Testing Machines Inc. S. I.: International System of Units

Note: All values shown are averages and should not be used for specification purposes.

Test data and test results contained in this document are for general information only and shall not be relied upon by Brady customers for designs and specifications, or be relied on as meeting specified performance criteria. Customers desiring to develop specifications or performance criteria for specific product applications should contact Brady for further information.

Product compliance information is based upon information provided by suppliers of the raw materials used by Brady to manufacture this product or based on results of testing using recognized analytical methods performed by a third party, independent laboratory. As such, Brady makes no independent representations or warranties, express or implied, and assumes no liability in connection with the use of this information.

WARRANTY

Brady products are sold with the understanding that the buyers will test them in actual use and determine for themselves their adaptability to their intended uses. Brady warrants to the buyers that its products are free from defects in material and workmanship, but limits its obligation under this warranty to replacement of the product shown to Brady's satisfaction to have been defective at the time Brady sold it. This warranty does not extend to any persons obtaining the product from the buyers. This warranty is in lieu of any other warranty, express or implied, including, but not limited to, any implied warranty of merchantability or fitness for a particular purpose, and of any other obligations or liability on Brady's part. Under no circumstances will Brady be liable for any loss, damage, expense, or consequential damages of any kind arising in connection with the use, or inability to use, Brady's products.

Copyright 2019 Brady Worldwide, Inc. | All Rights Reserved Material may not be reproduced or distributed in any form without written permission.

Brady North America | 6555 W. Good Hope Rd | Milwaukee, WI 53223 | USA | Tel: 414-358-6600 | Fax: 800-292-2289