



* does not represent actual color

SNL60-RXP Form-In-Place

A rapid cure, silver/aluminum-filled silicone elastomer Form-In-Place gasket material.

Laird Technologies introduces its newest line of FIP products—EMI Sentry. These Form-In-Place pastes are extremely fast curing with reliable shielding effectiveness and strength

Laird Technologies' Form-In-Place is an automated system for dispensing conductive elastomer EMI shielding and grounding gaskets onto metal or plastic substrates. This product is particularly ideal for basestations, PDAs, PC cards, radios, mobile phones, as well as many other cast or plastic enclosures and packaged electronic assemblies.

TYPICAL VALUES

	TEST METHOD	UNITS	SNL60-RXP
Elastomer			Silicone
Filler			Silver/Aluminum
ELECTRICAL PROPERTIES			
Volume Resistivity		ohm-cm	0.003
Shielding Effectiveness	MIL-DTL-83528C		
200 MHz to 10 GHz	Para. 4.5.12	dB	>100
PHYSICAL PROPERTIES			
Hardness	ASTM D2240	Shore A	60
Tensile Strength	ASTM D412	kPa	850
Tensile Elongation	ASTM D412	%	140
Density (cured)	ASTM D792	g/cm ³	2.1
Density (uncured)	LT-FIP-CLE-09	g/cm ³	1.8
Compression Set	ASTM D395	%	10
Adhesion Strength (Al)	LT-FIP-CLE-03	N/cm ²	140
Compression-Deflection (a)	LT-FIP-CLE-07		
at 20% compression		lb/in	1.9
at 40% compression		lb/in	8.3
Temperature Range		°C	-50°C to 125°C
UL rating	UL-94		V0
CURING REQUIREMENTS			
Cure Conditions		15°C to 40°C, 50% relative	
At 22°C and 50% RH	LT-FIP-CLE-14		
Time before handling			1 hour
Full Cure			24 hours

(a) Compression-deflection bead size 0.60 mm (H) x 0.75 mm (W)

rev. 07/02/09

global solutions: local support™

USA: +1 866 928.8181

Europe: +49 8031.2460.0

Asia: +86 755.2714.1166





SNL60-RXP Form-In-Place

A rapid cure, silver/aluminum-filled silicone elastomer Form-In-Place gasket material.

SNL60-RXP is one of the new products in the EMI Sentry line. This paste has dynamic shielding effectiveness, strength for environmental protection, and is a room temperature-cured paste. Products in the EMI Sentry line all have superior adhesion strength, strong reliability in low compression sets, as well as heat and humidity resistance.

SNL60-RXP
Shielding Effectiveness (dB)
Preliminary



EMI-DS-FIP-SNL60-RXP 0709

Any information furnished by Laird Technologies, Inc. and its agents is believed to be accurate and reliable. Responsibility for the use and application of Laird Technologies materials rests with the end user, since Laird Technologies and its agents cannot be aware of all potential uses. Laird Technologies makes no warranties as to the fitness, merchantability or suitability of any Laird Technologies materials or products for any specific or general uses. Laird Technologies shall not be liable for incidental or consequential damages of any kind. All Laird Technologies products are sold pursuant to the Laird Technologies' Terms and Conditions of sale in effect from time to time, a copy of which will be furnished upon request. © Copyright 2009 Laird Technologies, Inc. All Rights Reserved. Laird, Laird Technologies, the Laird Technologies Logo, and other marks are trade marks or registered trade marks of Laird Technologies, Inc. or an affiliate company thereof. Other product or service names may be the property of third parties. Nothing herein provides a license under any Laird Technologies or any third party intellectual property rights.